



Valve Regulated Lead-Acid Rechargeable Battery




BPL3.3-12

The battery is constructed by plates, separators, safety valves and container. Since the electrolyte is held by a glass-mat separator and plates, the battery can be used in any direction and position without leakage.

PERFORMANCE SPECIFICATIONS


Nominal Voltage(V).....	12 volts(6cells in series)
Nominal Capacity(Ah)	
20 Hour rate F.V.(1.75V/cell) (165mA to 10.50volts)	3.30Ah
10 Hour rate F.V.(1.75V/cell) (314mA to 10.50volts)	3.14Ah
5 Hour rate F.V.(1.75V/cell) (561mA to 10.50volts)	2.81Ah
30 Min rate F.V.(1.30V/cell) (3300mA to 7.80volts).....	1.65Ah
Approximate Weight.....	1350g(2.98lbs.)
Terminal	
Standard.....	Type T1
Optional.....	Type T2
Internal Resistance (Fully Charged Battery).....	<50m Ω
Maximum Discharge Current For 5 sec.(A).....	49.5A
Maximum Charge Current(A).....	0.99A
Ambient Temperature	
Charge.....	0°C(32°F)~40°C(104°F)
Discharge.....	-20°C(-4°F)~50°C(122°F)
Storage.....	-20°C(-4°F)~40°C(104°F)
Vibration test:	
Frequency: 16.7Hz	
Amplitude: 4mm	
Vibrate the battery horizontally or vertically for 60 minutes. The battery have no abnormality.	
Design Life:10 years for standby use at 20°C	
Case.....	ABS
Dimension(mm/inch)	
Length ±1.5mm.....	134/5.28
Width ±1.5mm.....	67/2.64
Container Height ±1.5mm.....	60/2.36
Total Height ±2.0mm.....	66/2.60
Application.....	UPS, Toy-Cars, Fishing Lights.

BPL3.3-12 Battery discharge characteristics (25 °C/77 °F)



Battery Charging Characteristics

(Typical example of charge characteristic for the standby use)




Charging Procedure


Application	Charging method	Charging Voltage at 20 °C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C/cell)	Max. charging current (CA)	Charging time 0.1CA, 20 °C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power source	Constant voltage & Constant current charging (with current restriction)	2.25~2.30	-3	0.3	24	20	0~40 (32~104°F)
For cycle service		2.40~2.50	-4	0.3	16	10	

Battery Life Characteristics of Cyclic Use


Testing Conditions : Discharge Current : 0.25C Amp (F.V. 1.7V/cell)
 Charging Current : 0.1C Amp
 Charging Volume : 120% OF Discharge Capacity
 Ambient Temperature : 20 °C (68 °F)



OUTER DIMENSIONS




TERMINAL TYPE



Constant power discharge characteristics at 25°C/77°F

Final Voltage	Discharge time									
	5Min	10Min	15Min	30Min	1Hr	3Hr	5Hr	10Hr	20Hr	
10.80V	107.5	80.8	65.4	39.4	22.8	9.6	6.6	3.71	1.94	
10.50V	124.5	87.5	68.5	40.9	23.5	9.8	6.7	3.76	1.98	
10.20V	132.0	90.7	70.6	41.8	23.9	9.9	6.8	3.78	1.99	
9.90V	138.1	92.9	72.2	42.4	24.2	10.0	6.8	3.79	1.99	
9.60V	142.4	94.7	73.6	42.8	24.5	10.0	6.8	3.79	1.99	

TERMINAL POSITION



B.B. BATTERY CO., LTD.

Web Site: <http://www.bb-battery.com>

USA:
 B&B BATTERY(USA) INC.
 6415 RANDOLPH ST.COMMERCE,
 CA,90040 U.S.A.
 TEL: 1-323-278-1900. 1-800-278-8599
 FAX: 1-323-278-1268
 E-Mail: sales@bb-battery.com

EUROPE:
 B&B BATTERY(EUROPE) B.V.
 3 WIJNGAARDVELD, 9300 AALST,BELGIUM
 TEL:(00)32-53781567
 FAX:(00)32-53781567
 E-Mail: hansdevriese@bb-battery.com

CHINA FACTORY:
 B.B. BATTERY CO., LTD.
 CHENG DONG TRIAL AREA,HUANG GANG,
 RAOPING, GUANG DONG,CHINA,515700
 TEL:86-768-7601001-2
 FAX:86-768-7601469
 E-Mail: maggy@bb-battery.com

HONG KONG:
 NATIONAL TRADING LTD.
 TEL:852-2301-3800
 FAX:852-2739-1182
 E-Mail: bbhk@hkstar.com

JAPAN:
 B&B BATTERY(JAPAN) CO., LTD.
 1375-11 NARAHARA-MACHI,HACHIOJI,
 TOKYO 193-0803,JAPAN.
 TEL:81-426-25-6375
 FAX:81-426-25-6375
 E-Mail: miyata@bb-battery.com

TAIWAN:
 B.B. BATTERY(TAIWAN) CO., LTD.
 TEL:886-6-502-5150
 FAX:886-6-589-8087
 E-Mail: maggy@bb-battery.com

