


1-800-383-7323 USA/CAN www.energizer.com

Eveready 1215





Industry Standard Dimensions



Chemical System: Zinc-Manganese Dioxide (Zn/MnO2)

(No Added Mercury or Cadmium)

Designation: ANSI-15D, IEC-R6

Battery Voltage: 1.5 Volts

Operating Temp: -18°C to 55°C (0°F to 130°F)

Average Weight: 15.0 grams (0.5 oz.)

Volume: 8.0 cubic centimeters (0.5 cubic inch)

Average Capacity: 1,100 mAh to 0.8 volts

(Rated capacity at 25 mA continuous at 21°C)

Cell: One No. 15 (size "AA")

Jacket: Metal


INTERNAL RESISTANCE VS. TEMPERATURE


The measurement is an approximation of the battery's actual internal resistance. It is sensitive to the loads and operator technique.

Schedule: Background Load 750 ohms

Pulse Load 4.0 ohms Pulse Duration 1 second

Temperature	Typical Ri (ohms)
45°C (113°F)	0.4
21°C (70°F)	0.5
0°C (32°F)	0.8
-21°C (-4°F)	5.0





Important Notice

This data sheet contains information specific to batteries manufactured at the time of its publication.

Contents herein do not constitute a warranty.


Copyright © Eveready Battery Co. - All rights reserved

Form No. EBC - 3109H Page 1 of 2

1-800-383-7323 USA/CAN www.energizer.com


Eveready 1215

Industry Standard Tests (21° C)









Important Notice

This data sheet contains information specific to batteries manufactured at the time of its publication.

Contents herein do not constitute a warranty.

Copyright $\ensuremath{\mathbb{C}}$ Eveready Battery Co. - All rights reserved

Form No. EBC - 3109H Page 2 of 2