
NICKEL CADMIUM BATTERIES: INDIVIDUAL DATA SHEET

P-140AS A size (KR17/50) Type: S

Dimensions (with tube)

(mm)



Specifications

	mm	inch
Diameter	17.0 +0/-0.7	0.67 +0/-0.03
Height	50.0 +0/-1.5	1.97 +0/-0.06
Approximate	Grams	Ounces
Weight	32g	1.13

Nominal Voltage			1.2V			
Discharge Capacity*		Average**	1530mAh			
		Rated (Min.)	1400mAh			
Approx. Internal impedance at 1000Hz at charged state			14mΩ			
Charge Standard Rapid***		Standard	140mA (0.1lt) x 16 hrs.			
		Rapid***	1400mA (1lt) x 1.5 hrs.			
Ambient Temperature		Standard	°C	°F		
	Charge		0°C to 45°C	32°F to 113°F		
		Rapid	10°C to 40°C	50°F to 104°F		
m du li		charge	-20°C to 65°C	-4°F to 149°F		
A Tem	Storage	< 2 years	-20°C to 35°C	-4°F to 95°F		
		< 6 months	-20°C to 45°C	-4°F to 113°F		


- * 0.2lt discharge capacity after charging at 0.1lt for 16 hours.
- ** For reference only.
- *** Refer to "Charge Methods for Ni-Cd Batteries"

Battery performance and cycle life are strongly affected by how they are used. In order to maximize battery safety, please consult Panasonic when determining charge / discharge specs, warning label contents and unit design.

Note: [It] was previously expressed as [C]. [It] is an IEC standard expression for the amount of charge or discharge current and is expressed as: It(A) = Cn (Ab)/4h

- [It] is the reference test current in ampres
- [Cn] is the rated capacity of the cell or battery in Ampere-hours.
 n = the time base [hours] for which the rated capacity is declared

Typical Charge Characteristics



Typical Discharge Characteristics

