3M

Heat Shrink Tubing FP-301

Flexible Polyolefin

		January 2008		
Product Description	3M TM Heat Shrink Tubing FP-301 offers an outstanding balance of electrical, physica and chemical properties for a wide variety of industrial and military applications Rated for 135°C continuous operation, all FP-301 Tubing is split resistant mechanically tough, easily marked and resists cold flow.			
	FP-301 Tubing meets MIL-DTL-23053/5 Class 1 & 2 and AMS-3636, AMS-3637 requirements. It is UL Recognized and CSA Certified at 600 volts @ 125°C (UL File Nos. E-39100 and CSA No. 38227).			
	FPS-301 Tubing is rated for continuous operation at -55°C (-67°F) to 135°C (275°F) and is designed to withstand elevated temperatures to 300°C (572°F) for short periods Minimum shrink temperature for all FP-301 Tubing is 100°C (212°F).			
Applications	FP-301 Tubing is typically used as a shrink-fit electrical insulation over cable splice and terminations. It is also used for lightweight wire harness covering, wire marking wire bundling, component packaging and fire-resistant covering.			
NOTE: Tashniasl informatic	on provided consists of typical product	data and should not be used for specification		
	merwise noted, all tests are performed MIL-DTL-23053/5, Class 1, 2; AMS			
purposes. Unless oth	nerwise noted, all tests are performed	at room temperature.		
purposes. Unless oth	merwise noted, all tests are performed MIL-DTL-23053/5, Class 1, 2; AMS	at room temperature.		
purposes. Unless oth Applicable Specification Typical Physical	MIL-DTL-23053/5, Class 1, 2; AMS CSALR38227; ABS	at room temperature. S-3636, AMS-3637; UL File E-39100;		
purposes. Unless oth Applicable Specification Typical Physical	MIL-DTL-23053/5, Class 1, 2; AMS CSALR38227; ABS Tensile Strength	at room temperature. S-3636, AMS-3637; UL File E-39100; 2400 psi		
purposes. Unless oth Applicable Specification Typical Physical	merwise noted, all tests are performed MIL-DTL-23053/5, Class 1, 2; AMS CSALR38227; ABS Tensile Strength Ultimate Elongation	2400 psi 400%		
purposes. Unless oth Applicable Specification Typical Physical	MIL-DTL-23053/5, Class 1, 2; AMS CSALR38227; ABS Tensile Strength Ultimate Elongation Longitudinal Change	at room temperature. S-3636, AMS-3637; UL File E-39100; 2400 psi 400% ±5%		
purposes. Unless oth Applicable Specification Typical Physical	MIL-DTL-23053/5, Class 1, 2; AMS CSALR38227; ABS Tensile Strength Ultimate Elongation Longitudinal Change Secant modulus (2%)	2400 psi 400% ±5% 13,000 PSI 1.3 (Black)		
purposes. Unless oth Applicable Specification Typical Physical	MIL-DTL-23053/5, Class 1, 2; AMS CSALR38227; ABS Tensile Strength Ultimate Elongation Longitudinal Change Secant modulus (2%) Specific Gravity	2400 psi 400% ±5% 13,000 PSI 1.3 (Black) .93 (Clear)		
purposes. Unless oth Applicable Specification Typical Physical	MIL-DTL-23053/5, Class 1, 2; AMS CSALR38227; ABS Tensile Strength Ultimate Elongation Longitudinal Change Secant modulus (2%) Specific Gravity Heat Aging (336 hrs. @ 175°C)	2400 psi 400% ±5% 13,000 PSI 1.3 (Black) .93 (Clear) Elongation 175% No dripping, flowing, cracking		

Typical Electrical Properties

Dielectric Strength 900 V/mil

Volume Resistivity 10¹⁵ ohm-cm

Typical Chemical Properties

Corrosive Effect Non-corrosive

Solvent Resistance

Tensile Strength 1000 PSI Dielectric Strength 400 V/mil

Water Absorption 0.2%

Fungus Resistance Non-nutrient

Standard Sizes and Dimensions

Ordering Size	Expanded I.D. (Minimum) in. (mm)	Recovered .I.D (Maximum) in. (mm)	Recovered Wall Thickness (Nominal) in. (mm)
3/64	.046 (1,17)	0.23 (0,58)	.016 (0,41)
3/16	.063 (1,60)	.031 (0.79)	.017 (0.43)
3/32	.093 (2,36)	.046 (1,17)	.020 (0,51)
1/8	.125 (3,18)	.062 (1,57)	.020 (0.51)
3/16	.187 (4,75)	.093 (2,36)	.020 (0,51)
1/4	.250 (6,35)	.125 (3,18)	.025 (0,64)
3./8	.375 (9,53)	.187 (4,75)	.025 (0,64)
1/2	.500 (12,70)	.250 (6,35)	.025 (0.64)
3/4	.750 (19,05)	.375 (9,53)	.030 (0,76)
1	1,000 (25,40)	.500 (12,70)	.035 (0.89)
1 1/2	1,500 (38,10)	.750 (19,05)	.040 (1,02)
2	2,000 (50,80)	1,000 (25,40)	.045 (1,14)
3	3,000 (76,20)	1,500 (38,10)	.050 (1,27)
4	4,000 (101,60)	2,000 (50,80)	.055 (1,40)

Shrink Ratio	3M TM Heat Shrink Tubing FP-301 has a 2:1 shrink ratio. When freely recovered, the polyolefin tubing will shrink to 50% of its as-supplied internal diameter. The recovered wall thickness of the tubing is proportional to the degree of recovery. High expansion-ratio FP-301 Tubing meeting MIL-DTL-23053/5 Class 1 requirements for overexpansion are available subject to factory quotation.	
Standard Colors	FP-301 Tubing, Class I (flame retardant) – black, white, red, blue, green (1/16"-1" green only) and yellow. FP-301, Class 2 (non-flame retardant)-clear. Other colors available subject to factory quotation.	
Standard Packaging	Four-foot lengths, large spools (21" diameter) and small spools (8 1/2" diameter).	
Ordering Information	Order FP-301 Tubing by product name, size equivalent to expanded inside diameter, package type and color. Always order the largest size that will shrink snugly over the item to be covered. Example: FP-301 Tubing, 1/4", 4 ft., white.	
Important Notice	All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.	
Warranty; Limited Remedy; Limited Liability:	This product will be free from defects in material and manufacture at time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.	

3M is a trademark of 3M Company.

Electrical Markets Division 6801 River Place Blvd. Austin, TX 78726-9000 800 676 8381 FAX 800 828 0329 www.3M.com/oem

Please recycle. Printed in U.S.A. © 3M 2008 All rights reserved. 78-8131-7399-0_A