


DATA SHEET

Product Number: 3157-0-00-15-00-00-03-0



Description:

3157 - Solderless Pressfit PCB

Packaging:

Packaged in Bulk

3157-0-00-XX-00-00-03-0

Press-fit in .026 mounting hole

Mill-Max Part Number	Shell Plating	Contact Plating	RoHS Compliant
3157-0-00-15-00-00-03-0	10 μ" Gold over Nickel	00	RoHS 2002/95/EC

SHELL MATERIAL:

BRASS ALLOY (UNS C36000) per ASTM B 16

Properties of BRASS ALLOY:

• Chemical composition: Cu 61.5%, Zn 35.4%, Pb 3.1%†

• Hardness as machined: 80-90 Rockwell B

• Density: .307 lbs/in3

• Electrical conductivity: 26% IACS*

• Melting point: 900°C/885°C (liquidus/solidus)

†(3 to 4% lead is used to permit "free machining" and is permitted by EC Directive 2002/95Annex 6; so all pin materials are RoHS compliant)

*International Annealed Copper Standard, i.e. as a % of pure copper.