

3M™ 2126R Cushioned Static Shielding Wrap Properties

Property	Test Method	Typical Value
Thickness	PPP-C 1842	125 mil
Strength		
Tensile	ASTM D882	34 lbs./in. width
Puncture	FTMS 101	22 lbs.
Surface Resistance/Resistivity		
Interior	ANSI/ESD S11.11	10^{12} ohms/sq.
Exterior	ANSI/ESD S11.11	$<10^{11}$ ohms
Metallized Layer	Monroe #267	$<10^2$ ohms/sq.
Shielding	EIA-541 (V-Zap)	$<30V$
Electrostatic Decay		
Interior	ANSI/ESD S11.11	<2 sec.
Contact Corrosivity	FTMS 101, Method 3005	Pass
Shelf life (from date of manufacture)		1 - Year