




## Features

- Trays that can stack and nest together for improved use of space
- Great container for Kanban



Item No.	Size I.D. - L x W x D
37750	18 x 11-3/8 x 1-3/4
37751	22-7/8 x 17-1/4 x 2-3/4

## SPECIFICATIONS

### Properties

#### Electrostatic Decay

#### Surface Resistivity

#### Surface Resistivity, Low R.H. Cut-off

#### High-Voltage Discharge Resistance

#### Static Shielding

#### Charged Device Model (CDM) Safety

#### Current-Carrying Hazard

#### Corrosivity

#### Antistat Transfer

#### Water & Isopropyl Alcohol Extraction Tests for Antistat Permanence

#### Sloughing Test

#### Recyclability

#### Biodegradability

#### Volume Conductivity

#### Shelf Life

### Typical Values

0.01 seconds at 72°F and 11.8% R.H.

$10^7$  -  $10^8$  ohms/sq. after 11 days at 68°F and 12% R.H. for surface.  $10^3$  -  $10^4$  ohms/sq. for buried shielding layer 4% R.H.

Failure rate 0/5 (no oxide damage in five consecutive tests)

99.9% attenuation at 10kV; 99.6% attenuation at 30kV

RTG  $>10^7$  ohms at 86% R.H. or less

$10^3$  mA at 110V;  $10^3$  mA at 220V

Contains 1-3 ppm reducible sulfur

No transfer

Surface resistivity  $10^8$  -  $10^9$  ohms/square at 74°F and 36% R.H.

Negligible surface damage at 10 cycles and <5% of surface damage at 200 cycles in Taber Abrasion Test.

No conductive particles abraded from surface

Complete recyclability of package

Biodegradation in or on moist soil

Conductivity from wall to wall as well as across surface to assure permanence of the antistatic property

Indefinite

### Test Procedures/Method

FED-STD-101, Method 4046

ASTM D257

Rockwell International Test Report of December 20, 1991

Rockwell International Test Report of December 20, 1991

EIA 541, appendix E, capacitive probe test

Rockwell International Test Report of December 20, 1991

ESD from A to Z

FED-STD-101, Method 3005 for reducible sulfur

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992

ASTM D4060 at 70 rpm with CS-17 abrasive-coated wheels and 1000 grams load

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992



Made in America

## TEK-TRAYS

# PROTEKTIVE PAK

PROTEKTIVE PAK  
13520 MONTE VISTA AVENUE CHINO, CA 91710  
PHONE (909) 627-2578, FAX (909) 363-7331  
www.protektivepak.com

**DRAWING NUMBER**  
37750

**DATE:**  
7/05