Dri-Shield 2000™

Moisture Barrier Bag ~ Aluminized

SCC's Dri-Shield 2000 Moisture Barrier Bag is designed for dry packaging of electronic devices and uses the first structure approved under MIL-PRF-81705 Type I. Dri-Shield 2000 bags are made from multiple layers of metallized polyester and dissipative polyethylene. Bags protect SMD's from moisture and static damage. Flexible structure is easy to vacuum seal. Coded for QC traceability.

Standards

Meets electrical and physical requirements of MIL-PRF-81705 Type 1, EIA 583, EIA 541, EIA 625, and EOS/ESD Standards.

Specifications

Physical Properties: Typical Values

MVTR(g/100 sq.in./24 hrs) <.02 ASTM F 1249
Puncture Resistance > 20 lbs FTMS 101 MTH 2065

Thickness 3.6 mils SCC 008
Tensile Strength 40 lb ASTM D882
Seam Strength Pass MIL-PRF-81705

Heat Sealing Conditions:

 Temperature
 300°F - 400°F

 Time
 0.6 - 4.5 seconds

 Pressure
 30 - 70 PSI

Electrical Properties:

Surface Resistivity / Resistance ASTM D257 or ANSI/ESD STM11.11 Interior $<10^{12}$ ohms/square or $<10^{11}$ ohms Exterior $<10^{12}$ ohms/square or $<10^{11}$ ohms

Metal 100 ohms

Static Shielding < 20 volts EIA 541

Static Shielding < 10 nJ EOS/ESD S11.31
EMI Attenuation 45 dB MIL-PRF-81705
Static Decay < 0.03 seconds FTMS 101 MTH 4046
Non-Corrosive Pass FTMS 101 MTH 3005

Outgassing Pass ASTM E595



Moisture Barrier Bag with Humidity Indicator Card and Desiccant





Material Structure

Multiple layers of metallized polyester provide puncture resistance and moisture barrier for this economical dry package. This highly reliable material meets or exceeds MVTR and


EMI/RFI/Static Shielding STATIC DISSIPATIVE POLYESTER

requirements of MIL-PRF-81705, Type I and EIA 583, Type I for static safe.

ALUMINUM SHIELD

moisture barrier packaging.

STATIC DISSIPATIVE
POLYETHYLENE



See SCC Data Sheets for these related items:

Humidity Indicator Cards (HIC's)

Desiccant Vacuum Sealers

PRODUCT DATA SHEET

Dri-Shield 2000 Moisture Barrier Bag ALUMINIZED

PRODUCT
MOISTURE BARRIER BAG, ALUMINIZED

TEM NUMBER 700(W")(L")

<u>DATASHEET</u> 1102-A



US and Canada: 866-722-3736

Fax: 866-722-3735 Intl: 919-774-3808 Fax: 919-774-1287

3010 Lee Avenue Sanford, NC 27330

email: info@staticcontrol.com www.**StaticControl**.com


Dri-Shield 2000™

Moisture Barrier Bag ~ Aluminized

W"x L"	P/N	W"x L" P/N	W"x L" P/N
3 x 5	70035	8 x 10 700810	14 x 30 7001430
4 x 6	70046	8 x 12 700812	15 x 18 7001518
4 x 24	700424	10 x 12 7001012	16 x 18 7001618
5 x 30	700530	10 x 20 7001020	17 x 19 7001719
6 x 8	70068	10 x 24 7001024	18 x 18 7001818
6 x 10	700610	10 x 30 7001030	18 x 24 7001824
6 x 24	700624	12 x 16 7001216	
6 x 30	700630	12 x 18 7001218	

- All standard sizes in-stock/same day shipment.
- Width is measured from inside seam to inside seam.
- Length is measured from the top edge to the bottom fold.
- Opening is in the "width" dimension.
- Custom bag sizes, custom printing, and custom hot stamping are available.
- Most sizes are packed 100 per case.
 Small sizes are packed 1000 or 500 per case.

Dri-Shield 2000



How Moisture Barrier Bags Work

Moisture barrier bags work by enclosing a device with a metal or plastic shield(s) that has a high resistance to moisture vapor permeation. Dry devices are placed inside this shield, and the moisture-laden air is evacuated. Desiccant filled pouches scavenge the remaining moisture from the bag's interior. Moisture that penetrates the bag is also entrapped by the desiccant. Humidity indicating cards report the effectiveness of the package upon device use. A label on the bag indicates the amount of exposure time devices are allowed prior to use, and the drying (re-baking) time and temperature if the exposure time is exceeded.

As the barrier property improves, the Moisture Vapor Transmission Rate (MVTR) decreases. Bags with lower MVTR provide better barrier. Aluminum foil provides the best MVTR of about 0.0003. Multiple layers of Aluminized Polyester can provide 0.02 to about 0.005.

Puncture Resistance is an important feature for barrier bags. Sharp tray edges may tear through bags with low puncture resistance.

PRODUCT DATA SHEE⁻

Dri-Shield 2000 Static Shielding Bag METAL-IN

PRODUCT
MOISTURE BARRIER BAG, ALUMINIZED

<u>ITEM NUMBER</u> 700(W")(L")

DATASHEET 1102-A



US and Canada: 866-722-3736

Fax: 866-722-3735 Intl: 919-774-3808 Fax: 919-774-1287

3010 Lee Avenue Sanford, NC 27330 email: info@staticcontrol.com

www.**StaticControl**.com

©