

3M™ 1900/1910 Metal-In Static Shielding Bag Properties

Property	Test Method	Typical Value
Thickness	ASTM D2103	2.9 mil
Strength		
Tensile	ASTM D882	18 lbs./in. width
Puncture	FTMS 101	>12 lbs.
Seal	MIL PRF 81705	Pass
Light Transmission	ANSI PH2.19	40%
Surface Resistance/Resistivity		
Interior	ANSI/ESD S11.11	<10 ¹¹ ohms
Exterior	ANSI/ESD S11.11	<10 ¹¹ ohms
Metallized Layer	Monroe #267	<10 ² ohms/sq.
Electrostatic Shielding	EIA-541 (V-Zap) ANSI/ESD S11.31	<30V <25nJ
Electrostatic Decay		
Interior	EIA-541	<2 sec.
Contact Corrosivity	FTMS 101, Method 3005	Pass
Outgassing		
TML	ASTM E595	<1.0%
CVCM	ASTM E595	<0.1%
Heat Seal Properties		
Temperature		180°F - 250°F
Time		0.5 - 5.0 Sec.
Pressure		20 60 PSI
Shelf Life (from date of manufacture)		1 - Year