3M Double Coated Urethane Foam Tapes 4004 • 4008 • 4016 • 4026 4032 • 4052 • 4056 • 4085

Technical Data			June, 2008
Product Description	3M TM Double Coated Urethane Foam Tapes are confo shear strength and are available with either a high ten adhesive system or a rubber adhesive system for bond for mounting, joining and holding.	nperature hold	ing acrylic
Products	Note: The user is responsible for determining whether purpose and suitable for user's method of application of the set of		or a particular
	3M™ Double Coated Urethane Foam Tape 4004	1/4 in.	(6.4 mm) thick
	3M™ Double Coated Urethane Foam Tape 4004 3M™ Double Coated Urethane Foam Tape 4008	1/4 in. 1/8 in.	
	3M [™] Double Coated Urethane Foam Tape 4008		(3.2 mm) thick
	-	1/8 in.	(3.2 mm) thick (1.6 mm) thick
	3M [™] Double Coated Urethane Foam Tape 4008 3M [™] Double Coated Urethane Foam Tape 4016	1/8 in. 1/16 in.	(3.2 mm) thick (1.6 mm) thick (1.6 mm) thick
	3M [™] Double Coated Urethane Foam Tape 4008 3M [™] Double Coated Urethane Foam Tape 4016 3M [™] Double Coated Urethane Foam Tape 4026	1/8 in. 1/16 in. 1/16 in.	(3.2 mm) thick (1.6 mm) thick (1.6 mm) thick (0.8 mm) thick
	3M [™] Double Coated Urethane Foam Tape 4008 3M [™] Double Coated Urethane Foam Tape 4016 3M [™] Double Coated Urethane Foam Tape 4026 3M [™] Double Coated Urethane Foam Tape 4032	1/8 in. 1/16 in. 1/16 in. 1/32 in.	(6.4 mm) thick (3.2 mm) thick (1.6 mm) thick (1.6 mm) thick (0.8 mm) thick (0.8 mm) thick (1.6 mm) thick

$3M^{\text{TM}}$ Double Coated Urethane Foam Tapes

4004 • 4008 • 4016 • 4026 • 4032 • 4052 • 4056 • 4085

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

		3M™ Double Coated Urethane Foam Tape			
	Units	4004	4008	4016	4026
Adhesive Type:*		100	100	100	100
Adhesive Carrier:		Polyurethane Foam	Polyurethane Foam	Polyurethane Foam	Polyurethane Foar
Thickness: Nominal	inch (mm)	0.250 (6.4)	0.125 (3.2)	0.0625 (1.6)	0.0625 (1.6)
Thickness: Tolerance:	inch (mm)	0.215-0.285 (5.46-7.24)	0.110-0.150 (2.79-3.81)	0.045-0.080 (1.142-2.03)	0.045-0.080 (1.142-2.03)
Color:		Natural	Natural	Natural	Natural
Release Liner:	inch (mm)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)
Liner Color:		Green Plaid	Green Plaid	Green Plaid	Green Plaid
Approximate Density: (Foam Only)	lb/ft³ (kg/m³)	12 (190)	15 (240)	11 (175)	18 (290)
Standard Length:	yard (meter)	18 (16.5)	36 (32.9)	36 (32.9)	36 (32.9)
Maximum Length:	yard (meter)	25 (23)	50 (45.7)	100 (91)	100 (91)
Available Width:	inch (mm)	46 (1168)	46 (1168)	46 (1168)	46 (1168)
Normal Slitting Tolerance:	inch (mm)	± 1/32 (± 0.8)	± 1/32 (± 0.8)	± 1/32 (± 0.8)	± 1/32 (± 0.8)
Normal Tensile: ("T" Block) 1 in² (6.45 cm²) Jaw Speed 2 in/min (50 mm/min)	psi (kPa)	12 (85)	25 (170)	50 (345)	40 (275)
Static Shear: Measured at various gram loadings. (1/2 sq. in. overlap). Will hold listed weight for 100 hours. Measured at various gram loadings. (1/2 sq. in. overlap). Measured at various (1/2 sq. in. overlap). (1/2 sq. in	gms	1000 500 500 250	1000 500 500 250	1500 1000 750 750	2000 1000 1000 750
Tensile Strength:	psi (kPa)	90 (620)	160 (1100)	140 (965)	180 (1240)
Elongation:	%	90	90	100	100
Temperature Resistance: Short Term (Minutes, Hours) Long Term (Days, Weeks)	°F (°C) °F (°C)	380 (193) 220 (104)	380 (193) 220 (104)	380 (193) 220 (104)	380 (193) 220 (104)
Solvent Resistance:		No apparent degradation when exposed to splash tests of most hydrocarbon solvents.			
UV Resistance:		No apparent degradation when exposed to 7 days in U.V. chamber.			
Cold Flex at -20°F (-30°C):		No cracki	ng when flexed arou	nd a 1/4 in. (6.4 mm	mandrel).
Thermal Conductivity:	BTU/hr/°F/ft²/ft (watt/metre Kelvin)	0.036 (0.062)	0.036 (0.062)	0.036 (0.062)	0.036 (0.062)
Dielectric Strength:	volts/mil (volts/0.025 mm)	200-300 (200-300)	200-300 (200-300)	200-300 (200-300)	200-300 (200-300)

*3M[™] Adhesive 100 is a firm acrylic pressure sensitive adhesive system. It features high ultimate bond strength, very good high temperature and solvent resistance and very high shear holding power. Bond strength increases substantially with natural aging.

3MTM Double Coated Urethane Foam Tapes

4004 • 4008 • 4016 • 4026 • 4032 • 4052 • 4056 • 4085

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

		3M™ Double Coated Urethane Foam Tape			
	Units	4032	4052	4056	4085
Adhesive Type:*		100	100	100	740
Adhesive Carrier:		Polyurethane Foam	Polyurethane Foam	Polyurethane Foam	Polyurethane Foan
Thickness: Nominal	inch (mm)	0.031 (0.8)	0.031 (0.8)	0.0625 (1.6)	0.045 (1.2)
Thickness: Tolerance:	inch (mm)	0.025-0.040 (0.64-1.02)	0.025-0.040 (0.64-1.02)	0.045-0.080 (1.142-2.03)	0.039-0.054 (1.00-1.45)
Color:		Natural	Black	Black	Natural
Release Liner:	inch (mm)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)
Liner Color:		Green Plaid	Green Plaid	Green Plaid	Tan
Approximate Density: (Foam Only)	lb/ft³ (kg/m³)	20 (320)	14 (225)	11 (175)	22 (352)
Standard Length:	yard (meter)	72 (65.8)	72 (65.8)	36 (32.9)	72 (65.8)
Maximum Length:	yard (meter)	175 (160)	175 (160)	100 (91)	100 (91)
Available Width:	inch (mm)	46 (1168)	46 (1168)	46 (1168)	46 (1168)
Normal Slitting Tolerance:	inch (mm)	± 1/32 (± 0.8)	± 1/32 (± 0.8)	± 1/32 (± 0.8)	± 1/32 (± 0.8)
Normal Tensile: ("T" Block) 1 in² (6.45 cm²) Jaw Speed 2 in/min (50 mm/min)	psi (kPa)	60 (414)	75 (515)	50 (345)	45 (310)
Static Shear: Measured at various temperatures and gram loadings. (1/2 sq. in. overlap). Will hold listed weight for 100 hours. T2°F (22°C) 120°F (49°C) 150°F (66°C) 200°F (93°C)	gms	2000 1500 1000 1050	1500 750 750 750	1500 1000 750 750	1000 250 —
Tensile Strength:	psi (kPa)	240 (1655)	225 (1550)	140 (965)	140 (965)
Elongation:	%	90	110	100	100
Temperature Resistance: Short Term (Minutes, Hours) Long Term (Days, Weeks)	°F (°C) °F (°C)	380 (193) 220 (104)	380 (193) 220 (104)	380 (193) 220 (104)	200 (93) 125 (152)
Solvent Resistance:		No apparent degradation when exposed to splash tests of most hydrocarbon solvents.			
UV Resistance:		No apparent degradation when exposed to 7 days in U.V. chamber.			
Cold Flex at -20°F (-30°C):		No cracki	ng when flexed arou	nd a 1/4 in. (6.4 mm	mandrel).
Thermal Conductivity:	BTU/hr/°F/ft²/ft (watt/metre Kelvin)	0.036 (0.062)	0.036 (0.062)	0.036 (0.062)	0.036 (0.062)
Dielectric Strength:	volts/mil (volts/0.025 mm)	200-300 (200-300)	200-300 (200-300)	200-300 (200-300)	200-300 (200-300)

*3M[™] Adhesive 100 is a firm acrylic pressure sensitive adhesive system. It features high ultimate bond strength, very good high temperature and solvent resistance and very high shear holding power. Bond strength increases substantially with natural aging.

3M[™] Adhesive 740 is a medium-firm rubber-resin pressure sensitive adhesive system. It features good holding power and adhesion to a wide variety of surfaces including many low surface energy plastics such as polyethylene and polypropylene.

3M[™] Double Coated Urethane Foam Tapes 4004 • 4008 • 4016 • 4026 • 4032 • 4052 • 4056 • 4085

Features	• The natural colored urethane foam tape products vary in color from white to light yellow. The color will change to light yellow upon exposure to sunlight (ultraviolet radiation). This color change is normal and does not affect tape performance.				
	• 3M [™] Double Coated Urethane Foam Tape 4026 is available in roll form and die- cut pieces. Die-cut pieces of 3M tape 4026 is available in 3/4" or 1" squares, either individual pieces double linered with an extended liner on one side or in pads of 48 squares.				
	• 3M [™] Double Coated Urethane Foam Tape 4085 combines conformability with high immediate adhesion to most plastics including ABS, polycarbonate, acrylic, polyethylene and polypropylene as well as metal and paint. 3M tape 4085 tears easily which makes it ideal for hand application.				
Application Techniques	• Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength.				
	• To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Typical surface cleaning solvents are isopropyl alcohol* and water (rubbing alcohol) or heptane.				
	• Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.				
	*Note: Be sure to follow the manufacturer's precautions and directions for use when using solvents.				
Application Ideas	The urethane foam tapes are generally ideal for interior applications or for exterior applications where the tape will be protected from the environment. The urethane foam is open cell.				
	 3MTM Double Coated Urethane Foam Tape 4004 – Bond mirrors to walls or furniture 3MTM Double Coated Urethane Foam Tape 4008 – Bond acoustic panels to walls 3MTM Double Coated Urethane Foam Tape 4016 – Mount interior signs and nameplates 3MTM Double Coated Urethane Foam Tape 4026 – Mount air fresheners and soap dispensers 3MTM Double Coated Urethane Foam Tape 4032 – Attach wire clips to various surfaces 3MTM Double Coated Urethane Foam Tape 4052 – Bond window to microwave oven doors Mount electrical channel to wall surfaces 3MTM Double Coated Urethane Foam Tape 4056 – Mount wall corner protectors 				
	3M TM Double Coated Urethane Foam Tape 4085 – Attach wire clips Attach air fresheners				

$\mathbf{3M}^{{}^{\scriptscriptstyle{\mathrm{TM}}}} \text{ Double Coated Urethane Foam Tapes}$

4004 • 4008 • 4016 • 4026 • 4032 • 4052 • 4056 • 4085

Storage	Store in original cartons at 70°F (21°C) and 50% relative humidity.	
Shelf Life	To obtain best performance, use these products within 24 months from date of manufacture except 3M [™] Double Coated Urethane Foam Tape 4085 which is 18 months from date of manufacture.	
Certification/ Recognition	MSDS: 3M has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.	
	TSCA: These products are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.	
Product Use	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.	
Warranty and Limited Remedy	Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individua products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNES FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.	
Limitation of Liability	Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.	
	This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards	



Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue St. Paul, MN 55144-1000 800-362-3550 • 877-369-2923 (fax) www.3M.com/industrial



Recycled Paper 40% pre-consumer 10% post-consumer

3M is a trademark of 3M Company. Printed in U.S.A. ©3M 2008 70-0705-7561-1 (6/08)